

TECHNICAL SHEET



Article:	B0168B TOLEDO
Norm:	EN ISO 20345:2012
Safety Class:	S1 P SRC
Footwear height:	Mod. A, H 85 mm (< 113 mm, Rif. EN ISO 20345-5.2.2)
Width:	11
Construction:	STROBEL; PU OUTSOLE
Cleaning and maintenance:	Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.
Suggested fields:	Mechanics, building, light industry, logistics.

Entire footwear: components				
Component	Description	Value	Norm requirements	EN 20345
Steel toe-cap	Impact resistance (200 J)			
	• Free height after impact	14,5 mm	≥ 14 mm	5.3.2.3
	Compression resistance (15 kN)			
	• Free height after compression	15 mm	≥ 14 mm	5.3.2.4
Sole (SRC)	Slip resistance			
	• SRA – sole (entire sole)	0,44	≥ 0,32	5.3.5.4
	• SRA – heel (angle of 7°)	0,42	≥ 0,28	5.3.5.4
	• SRB – sole (entire sole)	0,20	≥ 0,18	5.3.5.4
	• SRB – heel (angle of 7°)	0,18	≥ 0,13	5.3.5.4
	Fresh'n Flex (P)	Puncture resistance	No perforation	≥ 1100 N
Footbed (A)	Antistatic properties			
	• Electrical resistance	dry 10,0 x 10 ⁸ Ω humid 9,80 x 10 ⁸ Ω	≥ 10 ⁵ Ω , ≤ 10 ⁹ Ω ≥ 10 ⁵ Ω , ≤ 10 ⁹ Ω	6.2.2.2 6.2.2.2
Sole/upper heat (HI)	Thermal insulation			
	• Insole temperature increase	N/A	≤ 22°C	6.2.3.1
cold (CI)	• Insole temperature release	N/A	≤ 10°C	6.2.3.2
	heel (E)	Shock-absorption in the heel region	26 J	≥ 20 J
(WR)	Water resistance (water absorption)	N/A	≤ 3 cm ²	6.2.5
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6

Upper				
Component	Description	Value	Norm requirements	EN 20345
Suede leather	Tear resistance	168 N	≥ 60 N	5.4.3
	Traction resistance	16 N/mm ²	≥ 15 N/mm ²	5.4.4
	Water steam permeability	3,8 mg/cm ² h	≥ 0.8 mg/cm ² h	5.4.6
	pH value	4,05	≥ 3,2	5.4.7
	Chromium VI	Not detected	Not detectable	5.4.9
	Water passed	N/A	≤ 0.2 g	6.3
	Water absorption	N/A	≤ 30%	6.3

Lining				
Component	Description	Value	Norm requirements	EN 20345
3D hi-tech fabric	Tear resistance	30 N	≥ 15 N	5.5.1
	Abrasion resistance	<ul style="list-style-type: none"> Dry: the surface shows no hole Humid: the surface shows no hole 	No holes till 51.200 cycles	5.5.2
	Water steam release	7,2 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	pH value	N/A	Not detectable	5.5.4
	Chromium VI	N/A	Not detectable	5.5.5

Insole				
Component	Description	Value	Norm requirements	EN 20345
Fresh'n Flex	Thickness	3,5 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	109 mg/cm ²	≥ 70 mg/cm ²	5.7.3
	Water release	100 %	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	Not detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm requirements	EN 20345
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,5±0,5 mm	N/A	5.7.1
	Ph value	N/A	Not detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm ²	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	Nessun danno	Dry no holes till 25600 cycles Humid no holes till 12800 cycles	5.7.4.2
	Chromium VI	N/A	Not detectable	5.7.5

Sole					
Component	Description	Value	Norm requirements	EN 20345	
PU monodensity sole	Sole thickness without profile	9 mm	≥ 4 mm	5.8.1.1	
	Profile height	4 mm	≥ 2,5mm	5.8.1.3	
	Tear resistance	5,7 kN/m	≥ 5 kN/m	5.8.2	
	Abrasion resistance	<ul style="list-style-type: none"> Relative volume loss 	164 mm ³	≤ 250 mm ³	5.8.3
	Flexion resistance	<ul style="list-style-type: none"> Notches increase after 30.000 cycles 	1,5 mm	≤ 4 mm	5.8.4
	Hydrolysis	<ul style="list-style-type: none"> Notches increase after 150.00 cycles 	2 mm	≤ 6 mm	5.8.5
	Tread- Midsole detachment	N/A	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6	
	(HRO) contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1	
	(FO) fuel resistance (volume changes)	0,1 %	≤ 12%	6.4.2	

Date: 15/11/2016

Issued by: Resp.Tech. Eng. Cataldo De Luca

Signature:

